

Bascement Plus

CEM II/B-M (P-LL) 42,5 R

Bascement Plus is a Portland-composite cement produced by Heidelberg Materials in Slite, Sweden.

The product fulfills the technical data below. On rare occasions the values may deviate from the specified ranges or limits.

Property		Value	Range	Requirements in EN 197-1
Compact density (kg/m ³)		3023	±20	-
Bulk density (kg/m ³)		1000	±200	-
Setting time (min)		140	±30	≥ 60
Specific surface (blaine, m ² /kg)		-	±30	-
Brightness (%)		-	± 1	-
Compressive strength (MPa)	1 day	21	± 3	-
	2 days	33	± 3	≥ 20.0
	28 days	53	± 4	≥ 42.5 / ≤ 62.5
Sulfates, SO ₃ (%)		3.6	± 0.3	≤ 4.0
Alkali, Na ₂ O _{eq} (%)		1.1	± 0.1	-
Chlorides, Cl ⁻ (%)		0.06	± 0.03	≤ 0.10
Water-soluble chromium Cr ⁶⁺ (PPM)		0-2	-	≤ 2 ¹
Clinker (%)		≥ 68	-	65-79
Pozzolan (%)		≤ 22		6-29
Limestone (%)		≤ 12	-	6-29
Pozzolan + limestone (%)		≤ 32		21-35

¹ Clause 47 of Annex XVII the REACH Regulation.

The maximum storage period is 12 months from the date of packaging for unbroken big bags and 6 months from the date of delivery for silos (bulk).

For further information and handling of cement, see the safety data sheet.